

POF TECHNICAL FEATURES -1

PROPERTIES		13MICRONS	15MICRONS	19MICRONS	25MICRONS
Gloss at 20°		118			
Haze (%)		2.5			3
Shrinkage (%)	at 93°	30			
	at 120°	70			
Seal strength (N/30 mm)	at 120°	25	27	37	45
	at 150°	50	60	70	85
Water steam (g/m ² /24hr at 35c-		24	20	16	12
Oxygen		160000	13000	10000	8000
Roll length (m)	Singlewound BY-S	3100	2670	2140	1600
	Centerfold BY-C	1550	1335	1070	800
Internal diameter (mm)	76.2				
External diameter (mm)	245				